

Bioflex

High performance, mineral adhesive to fix vitrified tiles and natural stones on floor and wall.



1. Highly polymer modified
2. Thicknesses up to 15 mm
3. For internal and external use
4. For balconies and terraces
5. No sag
6. Prolonged workability
7. Adjustable
8. Sustains heat ageing
9. For fixing stones
10. Ideal for waterbodies (eg: fountains, swimming pools etc.)
11. Suitable for full body vitrified tiles

kerakoll

Areas of application

→ Intended use:

Substrates:

- cement-based screeds and mortars
- cellular concrete, for internal use
- plasterboard
- waterproofing products
- to overlay existing floors
- lime and cement-based plasters/renders
- fibro-cement slabs
- concrete surfaces
- screeds produced with Biocem
- mortar modified with Aquastop P6
- cement-based self-levelling products

Materials:

- ceramic tiles
- vitrified tiles
- terracotta
- marble and natural stone
- indian marble
- various mosaics
- internal insulating and soundproofing panels

Uses:

- adhesive and finishing
- for floors and walls
- internal use – external use
- overlaying
- terraces and balconies
- swimming pools and fountains
- saunas and SPA
- domestic applications
- commercial applications

Instructions for use

→ Preparation of the substrate

All surfaces must be dimensionally stable according to IS 1443-1972, level, cured, undamaged, compact, rigid, resistant, dry and free from any debonding agents and from damp rising.

It is good practice to dampen highly absorbent concrete substrates or apply a coat of suitable primer.

→ Adhesive preparation

Mixing water:

- ≈ 5 – 6 litres per 20 kg bag
- ≈ 7.5 – 9 litres per 30 kg bag

The amount of water indicated on the packaging is indicative. It is possible to obtain mixtures with consistency of variable thixotropy according to the application to be made.

→ Application

To guarantee maximum adhesion it is necessary to apply a sufficient layer of adhesive.

Large, rectangular sizes with sides > 60 cm may require adhesive to be applied directly to the back of the tile surface.

Check samples to make sure the adhesive has been transferred to the back of the material.

Create elastic expansion joints:

- ≈ 10 m² in external applications,
- ≈ 25 m² in internal applications,
- every 8 metres in long, narrow applications.

Respect all structural, fractionizing and perimeter joints present in the substrates.

Special notes

→ Pre-treatment of special substrates

Gypsum-based plasters/renderers: suitable primer.

→ Materials and special substrates

Marble, natural stones and recomposed materials that are subject to deformation or staining due to water absorption require a reactive adhesive. Marble, natural stones and recomposed materials in general may have characteristics that vary even with reference to materials of the same chemical and physical nature. For this reason it is essential you consult Kerakoll India Helpline to request specific indications or to carry out a test on a sample of the material.

In the absence of specific indications from the manufacturer, natural stone slabs with reinforcement layers, in the form of resin coating, polymer mesh, matting, etc. or treatments (for example damp courses, etc.) applied on the fixing surface must be tested in advance to ensure they are compatible with the adhesive.

Check for the presence of any really consistent traces of rock dust created during cutting, and remove them if found.

→ Special applications

Insulating and soundproofing panels for interior use applied using spot adhesion as recommended by the manufacturers. Plasterboard and fibro-cement slabs must be firmly anchored to specific metal frames.

→ Do not use

On wood, metal, plastics, resilient materials, deformable substrates.

On substrates subject to vibrations.

On non-cured screeds, plaster/renderers or concrete.

On plasterboard and fibre-cement slabs without priming.

Certificates and marks



* Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

Technical Data compliant with Kerakoll Quality Standard		
Shelf life	≈ 12 months in the original packaging. Protect from humidity.	
Pack	20 kg and 30 kg bags	
Adhesive thickness	up to 15 mm	
Temperature of the air, substrates and materials	from +5 °C to +35 °C	
Pot life at +23 °C	≈ 6 hrs	
Pot life at +35 °C	≈ 4 hrs	
Open time at +27 °C (BIII tile)	≥ 30 min.	EN 12004
Correction time at +27 °C (BIII tile)	≥ 50 min.	EN 12004
Foot traffic/grouting of joints at +23 °C (BIa tile):		
- Grey	≈ 20 hrs	EN 14411
- White	≈ 20 hrs	EN 14411
Foot traffic/grouting of joints at +35 °C (BIa tile):		
- Grey	≈ 12 hrs	EN 14411
- White	≈ 12 hrs	EN 14411
Grouting in walls at +23 °C (BIa tile)		
- Grey	≈ 20 hrs	EN 14411
- White	≈ 12 hrs	EN 14411
Grouting in walls at +35 °C (BIa tile):		
- Grey	≈ 12 hrs	EN 14411
- White	≈ 12 hrs	EN 14411
Ready for use at +23 °C / +35 °C (BIa tile):		
- light foot traffic	≈ 3 – 2 days	EN 14411
- heavy traffic	≈ 4 – 3 days	EN 14411
- swimming pools (+23 °C)	≈ 14 days	EN 14411
Consumption per mm of thickness:		
- Grey	≈ 1.3 kg/m ²	
- White	≈ 1.2 kg/m ²	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate and of the materials laid.

Performance		
VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions		
Conformity	EC 1 plus GEV-Emicode	GEV certified 4616/11.01.02
HIGH-TECH		
Tensile adhesion strength (dry condition)	≥ 2.5 N/mm ²	IS 15477:2019
Tensile adhesion strength (wet condition)	≥ 1 N/mm ²	IS 15477:2019
Shear adhesion strength (dry condition)	≥ 1.5 N/mm ²	IS 15477:2019
Shear adhesion strength (heat ageing)	≥ 1 N/mm ²	IS 15477:2019
Shear adhesion strength (wet condition)	≥ 1 N/mm ²	IS 15477:2019
Durability test:		
- adhesion after heat ageing	≥ 2.5 N/mm ²	EN 12004-2
- adhesion after water immersion	≥ 1 N/mm ²	EN 12004-2
- adhesion after freeze-thaw cycles	≥ 1 N/mm ²	EN 12004-2
- adhesion after straining cycles	≥ 1 N/mm ²	SAS Technology
Vertical slip	≤ 0.5 mm	EN 12004-2
Working temperature	-30 °C to +90 °C	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

- Abide by any standards and national regulations

→ do not use the adhesive to correct substrate irregularities greater than 15 mm

→ protect from direct rainfall for at least 24 hrs

→ the temperature, ventilation and absorption of the substrate and covering materials, may vary the adhesive workability and setting times
- use the right size of notched trowel for the format of the tile or slab

→ guarantee a full-bed in all external laying operations

→ if necessary, ask for the safety data sheet

→ for any other issues, contact the Kerakoll India Helpline (Toll Free) 1800 102 4957 – info@kerakollindia.com

This information was last updated in August 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.